



Material - SAE Waspaloy

Standard Specification for Nickel Alloy, Corrosion and Heat-Resistant, Bars, Forgings and Rings

Group - Non-Ferrous Nickel Alloys

Sub Group - SAE Waspaloy Nickel Alloy, Corrosion and Heat-Resistant, Bars, Forgings and Rings

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Bar, Forging and Ring

Chemical Composition			Heat Treatment	
Carbon	C %	0.020 - 0.100	As-Cast or Annealing or Age Hardning	
Silicon	Si %	0.150 max.		
Manganese	Mn %	0.100 max.		
Chromium	Cr %	18.000 - 21.000		
Sulphur	S %	0.015 max.		
Molybdenum	Mo %	3.500 - 5.000		
Phosphorus	P %	0.015 max.		
Cobalt	Co %	12.000 - 15.000		
Copper	Cu %	0.100 max.		
Aluminium	Al %	1.200 - 1.600		
Boron	B %	0.003 - 0.010		
Titanium	Ti %	2.750 - 3.250		
Zirconium	Zr %	0.020 - 0.080		
Iron	Fe %	2.000 max.		
Nickel	Ni %	Balance		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
WASPALOY	Gravity	India	Pipe, Tube, Sheet, Strip, Plate, Hexagon and Wire
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.