



## Material - SFS CuPb1P

## Standard Specification for Copper and Copper Alloy Rod for Free Machining Purpose

**Group - Non Ferrous Copper Alloys** 

Sub Group - SFS CuPb1P Copper and Copper Alloy Rod for Free Machining Purpose
Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries
Grade Belongs to the Industry - Rod

Chemical Composition			Heat Treatment	
Phosphorus	P %	0.003 - 0.012		
Lead	Pb %	0.700 - 1.500		
Other	Ot %	0.100 max.		
Copper	Cu %	Balance	As Raw or Solution Heat Treated	
-	-	-		
-	-	-		
-	-	-		
-	-	-		-
-	-	-	Mechanical Properties	
-	-		Tensile Strength in Mpa	250 min.
-	-	-	Yield Strength in Mpa	180 min.
-	-	-	Elongation in %	5 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	80 - 130
-	-	-	Impac <mark>t in Joule</mark>	-

Cross Reference Table					
Material	Standard	Country	Grade Belong to the Industry		
EN 12164 CuPb1P	DIN	Germany	Rod		
CuPb1P	ONORM	Australia	Rod		
CW113C	ONORM	Australia	Rod		
2.116	DIN	Germany	Rod		
CuPb1P	AFNOR NF	France	Rod		
CW113C	AFNOR NF	France	Rod		
CW113C	SFS	Finland	Rod		

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.