



## Material - SFS CuZn40Pb2

**Standard Specification for Copper and Copper Alloy Rod for Free Machining Purpose**

**Group - Non Ferrous Copper Alloys**

**Sub Group - SFS CuZn40Pb2 Copper and Copper Alloy Rod for Free Machining Purpose**

**Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries**

**Grade Belongs to the Industry - Rod**

Chemical Composition			Heat Treatment	
Aluminium	Al %	0.100 max.	As Raw or Solution Heat Treated	
Iron	Fe %	0.400 max.		
Nickel	Ni %	0.400 max.		
Lead	Pb %	1.500 - 2.500		
Tin	Sn %	0.300 max.		
Other	Ot %	0.200 max.		
Copper	Cu %	57.000 - 59.000		
Zinc	Zn %	Balance		
-	-	-	<b>Mechanical Properties</b>	
-	-	-	Tensile Strength in Mpa	340 min.
-	-	-	Yield Strength in Mpa	140 min.
-	-	-	Elongation in %	5 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	70 - 160
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
EN 12164 CuZn40Pb2	DIN	Germany	Rod
B 124 CW617N	ASTM	USA	Rod
CuZn40Pb2	ISO	International	Rod
LS59-2	GOST	Russia	Rod
CW617N	SFS	Finland	Rod
CuZn40Pb2	BS	British	Rod
CW617N	BS	British	Rod

**Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email [marketing@gravitycastindia.com](mailto:marketing@gravitycastindia.com)**

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.