



Material - UNE 38211 L-2110

Standard Specification for Aluminium and Aluminium Alloy for moulding

Group - Non-Ferrous Alumium Alloy

Sub Group - UNE 38211 Aluminium and Aluminium Alloy for Moulding

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Copper	Cu %	9.200 - 10.800		
Iron	Fe %	1.500 max.		
Magnesium	Mg %	0.200 - 0.350	As-Cast	
Manganese	Mn %	0.500 max.		
Nickel	Ni %	0.300 max.		
Silicon	Si %	1.000 max.		
Lead	Pb %	0.100 max.		
Tin	Sn %	0.100 max.		
Titanium	Ti %	0.200 max.	Mechanical Properties	
Zinc	Zn %	0.800 max.	Tensile Strength in Mpa	160 - 275
Other	Ot%	0.300 max.	Yield Strength in Mpa	-
Aluminium	Al %	Balance	Elongation in %	-
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in HB	65 - 155
-	-	-	Impac <mark>t in Joule</mark>	-

Cross Reference Table				
Material	Standard	Country	Grade Belong to the Industry	
SB-26 222.0	ASME	USA	Casting	
222.0	AA	USA	Ingot and Casting	
B 275 CG100A	ASTM	USA	Casting	
A02220	UNS	USA	Casting	
LM12	BS	British	Ingot and Casting	
2550	IS	India	Ingot and Casting	
A02220	SAE	USA	Casting	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.