



Material - UNE CuNi12Zn30Pb1

Standard Specification for Copper and Copper Alloy Rod

Group - Non Ferrous Copper Alloys

Sub Group - UNE CuNi12Zn30Pb1 Copper and Copper Alloy Rod

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Rod

Chemical Composition			Heat Treatment	
Iron	Fe %	0.300 max.	As Raw or Solution Heat Treated	
Manganese	Mn %	0.500 max.		
Nickel	Ni %	11.000 - 13.000		
Lead	Pb %	0.500 - 1.500		
Tin	Sn %	0.200 max.		
Other	Ot %	0.200 max.		
Copper	Cu %	56.000 - 58.000		
Zinc	Zn %	Balance		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
			Mechanical Properties	
			Tensile Strength in Mpa	420 min.
			Yield Strength in Mpa	260 min.
			Elongation in %	6 min.
			Reduction of Area in %	-
			Hardness in BHN	110 - 180
			Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
CuNi12Zn30Pb1	DIN	Germany	Rod
Ns5712Pb	DIN	Germany	Rod
2.078	DIN	Germany	Rod
CuNi12Zn30Pb1	BS	British	Rod
CW406J	BS	British	Rod
CW406J	UNE	Spain	Rod
CW406J	NS	Norway	Rod

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.