



Material - UNE CuSn4Te1P

Standard Specification for Copper-Tin Alloy Rod

Group - Non Ferrous Copper Alloys

Sub Group - UNE CuSn4Te1P Copper-Tin Alloy Rod

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Rod

Chemical Composition			Heat Treatment	
Iron	Fe %	0.100 max.	As Raw or Solution Heat Treated	
Nickel	Ni %	0.200 max.		
Phosphorus	P %	0.100 - 0.400		
Tellurium	Te %	0.500 - 1.000		
Tin	Sn %	4.000 - 5.000		
Zinc	Zn %	0.300 max.		
Other	Ot %	0.200 max.		
Copper	Cu %	Balance		
-	-	-	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	380 min.
-	-	-	Yield Strength in Mpa	300 - 400
-	-	-	Elongation in %	5 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	160 max.
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
CuSn4Te1P	DIN	Germany	Rod
CuSn4Te1P	BS	British	Rod
CW457K	BS	British	Rod
CuSn4Te1P	SS	Sweden	Rod
CW457K	SS	Sweden	Rod
CuSn4Te1P	PN	Poland	Rod
CW457K	PN	Poland	Rod

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.