



Material - UNE EN 1706 AC-21100

Standard Specification for Aluminium and Aluminium Alloys - Castings

Group - Non-Ferrous Aluminium Alloy

Sub Group - UNE EN 1706 Aluminium and Aluminium Alloys - Castings

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Copper	Cu %	4.500 - 5.200	As-Cast or Solution Anneling and Aging	
Iron	Fe %	0.190 max.		
Manganese	Mn %	0.550 max.		
Silicon	Si %	0.180 max.		
Titanium	Ti %	0.150 - 0.300		
Zinc	Zn %	0.070 max.		
Other	Ot%	0.100 max.		
Aluminium	Al %	Balance		
-	-	-	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	280 - 450
-	-	-	Yield Strength in Mpa	180 - 400
-	-	-	Elongation in %	3 - 20
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in HB	85 - 145
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
EN AC-21100	ASME	USA	Casting
EN AC-21100	DIN	Germany	Casting
Al Cu4Ti	ISO	International	Casting
EN AC-21100	SFS	Finland	Casting
EN AC-21100	MSZ	Hungary	Casting
EN AC-21100	AFNOR NF	France	Casting
EN AC-21100	BDS	Bulgaria	Casting

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.