



Material - UNE EN 1982 CuZn34Mn3Al2Fe1-B

Standard Specification for Copper and Copper Alloys - Ingots and Castings

Group - Non-Ferrous Copper Alloy

Sub Group - UNE EN 1982 Copper and Copper Alloys - Ingots and Castings

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Ingot and Casting

Chemical Composition			Heat Treatment	
Aluminium	Al %	1.500 - 3.000		
Iron	Fe %	0.800 - 2.000	As-Cast	
Manganese	Mn %	1.000 - 3.500		
Nickel	Ni %	2.700 max.		
Phosphorus	P %	0.020 max.		
Lead	Pb %	0.200 max.		
Antimony	Sb %	0.050 max.		
Silicon	Si %	0.080 max.		
Tin	Sn %	0.300 max.	Mechanical Properties	
Cu + Ni	Cu%+Ni%	55.000 - 65.000	Tensile Strength in Mpa	600 - 620
Zinc	Zn %	Balance	Yield Strength in Mpa	250 - 260
-	-	-	Elongation in %	10 - 15
-	-	-	Reduction of Area in %	•
-	-	-	Hardness in HB	140 - 150
-	-	-	Impac <mark>t in Joule</mark>	-

Cross Reference Table				
Material	Standard	Country	Grade Belong to the Industry	
CC764S	BS	British	Ingot and Casting	
CB764S	AFNOR NF	France	Ingot and Casting	
CB764S	BDS	Bulgaria	Ingot and Casting	
CB764S	CSN	Czech Republic	Ingot and Casting	
CB764S	DIN	Germany	Ingot and Casting	
CuZn34Mn3Al2Fe1-B	UNI	Italy	Ingot and Casting	
CuZn34Mn3Al2Fe1-B	MSZ	Hungary	Ingot and Casting	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.