



GRAVITY CAST PVT. LTD.
GRAVITY GROUP OF COMPANIES

Material - UNE ZP0010

Standard Specification For Zinc and Zinc Alloy Castings

Group - Non-Ferrous Zinc Alloys

Sub Group - UNE ZP0010 Zinc and Zinc Alloy Castings

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Aluminium	Al %	0.010 - 0.040	As-Cast	
Copper	Cu %	1.000 - 1.500		
Magnesium	Mg %	0.020 max.		
Chromium	Cr %	0.100 - 0.200		
Titanium	Ti %	0.150 - 0.250		
Lead	Pb %	0.005 max.		
Cadmium	Cd %	0.005 max.		
Tin	Sn %	0.004 max.		
Iron	Fe %	0.050 max.		
Silicon	Si %	0.050 max.		
Zinc	Zn %	Balance	Mechanical Properties Tensile Strength in Mpa 220 min. Yield Strength in Mpa - Elongation in % - Reduction of Area in % - Hardness in HB - Impact in Joule -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
ZP16	DIN	Germany	Casting
ZP16	UNI	Italy	Casting
ZP16	BS	British	Casting
ZP0010	DIN	Germany	Casting
-	-	-	-
-	-	-	-
-	-	-	-

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.

ONE STOP SOLUTION FOR METAL PARTS