



## Material - UNE ZnAl4Cu3

## **Standard Specification For Zinc Alloy Ingots**

**Group - Non-Ferrous Zinc Alloys** 

Sub Group - UNE ZnAl4Cu3 Zinc Alloy Ingots

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

**Grade Belongs to the Industry - Ingot** 

Chemical Composition			Heat Treatment	
Aluminium	Al %	3.800 - 4.200	As-Cast	
Copper	Cu %	2.700 - 3.300		
Magnesium	Mg %	0.035 - 0.060		
Cadmium	Cd %	0.003 max.		
Tin	Sn %	0.001 max.		
Iron	Fe %	0.020 max.		
Lead	Pb %	0.003 max.		
Silicon	Si %	0.020 max.		
Nickel	Ni %	0.001 max.	Mechanical Properties	
Zinc	Zn %	Balance	Tensile Strength in Mpa	335 min.
-	-	-	Yield Strength in Mpa	270 min.
-	-	-	Elongation in %	5 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in HB	102 min.
-	-	-	Impact in Joule	59 J @ RT

Cross Reference Table				
Material	Standard	Country	Grade Belong to the Industry	
ZP2	DIN	Germany	Casting	
G-ZnAl4Cu3	UNI	Italy	Ingot	
B 240 AC43A	ASTM	USA	Ingot and Casting	
GB-ZnAl4Cu3	DIN	Germany	Ingot and Casting	
GK-ZnAl4Cu3	DIN	Germany	Casting	
2.2143	DIN	Germany	Casting	
2.2143.01	DIN	Germany	Casting	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.