



Material - UNI EN 1706 AC-ALSi9Mg

Standard Specification for Aluminium and Aluminium Alloys - Castings

Group - Non-Ferrous Aluminium Alloy

Sub Group - UNI EN 1706 Aluminium and Aluminium Alloys - Castings

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Copper	Cu %	0.050 max.	As-Cast or Solution Anneling and Aging	
Iron	Fe %	0.190 max.		
Magnesium	Mg %	0.200 - 0.450		
Manganese	Mn %	0.100 max.		
Silicon	Si %	9.000 - 10.000		
Titanium	Ti %	0.150 max.		
Zinc	Zn %	0.070 max.		
Other	Ot%	0.100 max.		
Aluminium	Al %	Balance		
-	-	-		
			Mechanical Properties	
			Tensile Strength in Mpa	160 - 230
			Yield Strength in Mpa	80 - 310
			Elongation in %	44471
			Reduction of Area in %	-
			Hardness in HB	50 - 120
			Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
EN AC-ALSi9Mg	DIN	Germany	Casting
EN AC-ALSi9Mg	BS	British	Casting
EN AC-ALSi9Mg	UNE	Spain	Casting
Al Si9Mg	ISO	International	Casting
EN AC-ALSi9Mg	SFS	Finland	Casting
EN AC-ALSi9Mg	AFNOR NF	France	Casting
EN AC-ALSi9Mg	MSZ	Hungary	Casting

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.