



Material - UNI EN 1706 G AlSi12MnMg

Standard Specification for Primary Aluminium-Silicon-Magnesium Alloy for Casting

Group - Non-Ferrous Aluminium Alloy

Sub Group - UNI EN 1706 Primary Aluminium-Silicon-Magnesium Alloy for Casting

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Copper	Cu %	0.100 max.	As-Cast or Annealing or Quenching	
Magnesium	Mg %	0.270 - 0.400		
Silicon	Si %	11.500 - 13.000		
Iron	Fe %	0.800 max.		
Manganese	Mn %	0.350 - 0.650		
Nickel	Ni %	0.100 max.		
Zinc	Zn %	0.100 max.		
Titanium	Ti %	0.100 max.		
Other	Ot%	0.300 max.		
Aluminium	Al %	Balance		
-	-	-	Mechanical Properties Tensile Strength in Mpa 215.7 - 313.8 Yield Strength in Mpa 177 - 275 Elongation in % 1 - 4 Reduction of Area in % - Hardness in HB 80 - 110 Impact in Joule -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
LM9	BS	British	Ingot and Casting
4635	IS	India	Ingot and Casting
G-AS12MG	UNI	Italy	Ingot and Casting
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.