



Material - UNI EN 1982 CuZn32Al2Mn2Fe1-B

Standard Specification for Copper and Copper Alloys - Ingots and Castings

Group - Non-Ferrous Copper Alloy

Sub Group - UNI EN 1982 Copper and Copper Alloys - Ingots and Castings

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Ingot and Casting

Chemical Composition			Heat Treatment	
Aluminium	Al %	1.000 - 2.500	As-Cast	
Iron	Fe %	0.500 - 2.000		
Manganese	Mn %	1.000 - 3.500		
Nickel	Ni %	2.500 max.		
Lead	Pb %	1.500 max.		
Antimony	Sb %	0.080 max.		
Silicon	Si %	1.000 max.		
Tin	Sn %	1.000 max.		-
Cu + Ni	Cu%+Ni%	59.000 - 67.000	Mechanical Properties	
Zinc	Zn %	Balance	Tensile Strength in Mpa	430 - 450
-	-		Yield Strength in Mpa	150 - 340
-	-	-	Elongation in %	3 - 10
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in HB	100 - 110
-	-	-	Impac <mark>t in Joule</mark>	-

Cross Reference Table				
Material	Standard	Country	Grade Belong to the Industry	
CC763S	BS	British	Ingot and Casting	
CB763S	CSN	Czech Republic	Ingot and Casting	
CB763S	BDS	Bulgaria	Ingot and Casting	
CB763S	AFNOR NF	France	Ingot and Casting	
CuZn32Al2Mn2Fe1-B	DIN	Germany	Ingot and Casting	
CuZn32Al2Mn2Fe1-B	ONORM	Australia	Ingot and Casting	
CuZn32Al2Mn2Fe1-B	MSZ	Hungary	Ingot and Casting	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.