



Material - UNI 9222 P-CuNi12Zn24

Standard Specification for Wrought copper Alloys, Copper-Nickel- Zinc and Copper-Nickel-Zinc-Lead Alloys

Group - Non-Ferrous Copper Alloy

Sub Group - UNI 9222 Wrought copper Alloys, Copper-Nickel- Zinc and Copper-Nickel-Zinc-Lead Alloys

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Rod and Bar

Chemical Composition			Heat Treatment	
Iron	Fe %	0.300 max.	Normalizing or Annealing or Tempering	
Manganese	Mn %	0.500 max.		
Nickel	Ni %	11.000 - 13.000		
Other	Ot%	0.300 max.		
Lead	Pb %	0.050 max.		
Copper	Cu %	62.000 - 65.000		
Zinc	Zn %	Balance		
-	-	-	Mechanical Properties Tensile Strength in Mpa 485 min. Yield Strength in Mpa - Elongation in % - Reduction of Area in % - Hardness in BHN - Impact in Joule -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
CuNi18Zn20	IS	India	Rod and Bar
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.