



Material - UNI EN 1706 AC- 51200

Standard Specification for Aluminium and Aluminium Alloys - Casting

Group - Non-Ferrous Aluminium Alloy

Sub Group - UNI EN 1706 Aluminium and Aluminium Alloys - Casting

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Copper	Cu %	0.100 max.	As-Cast	
Iron	Fe %	1.000 max.		
Magnesium	Mg %	8.000 - 10.500		
Manganese	Mn %	0.550 max.		
Nickel	Ni %	0.100 max.		
Silicon	Si %	2.500 max.		
Titanium	Ti %	0.200 max.		
Lead	Pb %	0.100 max.		
Tin	Sn %	0.100 max.		
Beryllium	Be %	0.005 max.		
Zinc	Zn %	1.500 max.	Mechanical Properties Tensile Strength in Mpa 160 - 180 Yield Strength in Mpa 100 - 110 Elongation in % 3 min. Reduction of Area in % - Hardness in HB 60 - 65 Impact in Joule -	
Other	Ot%	0.250 max.		
Aluminium	Al %	Balance		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
EN AC-51200	DIN	Germany	Casting
EN AC-51200	BS	British	Casting
EN AC-51200	ASME	USA	Casting
EN AC-51200	AFNOR NF	France	Casting
EN AC-51200	UNE	Spain	Casting
Al Mg9	ISO	International	Casting
EN AC-51200	SFS	Finland	Casting

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.