



Material - UNS 61900

Standard Specification for Copper and Copper Alloy Forging Rod, Bar and Shapes

Group - Non-Ferrous Copper Alloy

Sub Group - UNS Copper and Copper Alloy Forging Rod, Bar and Shapes

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Rod, Bar and Shape

Chemical Composition			Heat Treatment	
Aluminium	Al %	8.500 - 10.000		
Iron	Fe %	3.000 - 4.500	<u> </u>	
Lead	Pb %	0.020 max.	Normalizing or Annealing or Tempering	
Tin	Sn %	0.600 max.		ing or Tempering
Zinc	Zn %	0.800 max.		
Cu + Ag	Cu% + Ag%	Balance		
-	-	-		
-	-	-		_
-	-	-	Mechanical Properties	
-	-		Tensile Strength in Mpa	565 min.
-	-	-	Yield Strength in Mpa	255 min.
-	-	-	Elongation in %	32 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in HRB	82 min.
-	-	-	Impac <mark>t in Joule</mark>	-

Cross Reference Table				
Material	Standard	Country	Grade Belong to the Industry	
B124 C61900	UNS	USA	Rod, Bar and Shapes	
B150 C61900	ASTM	USA	Rod, Bar and Shape	
B283 C61900	ASTM	USA	Forging	
SB-150 C61900	ASME	USA	Forging	
SB-283 C61900	ASME	USA	Forging	
C 6191 BD	JIS	Japan	Rod and Bar	
-	-	-	-	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.