



## Material - UNS C37710

### Standard Specification for Copper and Copper Zinc Alloy Rod

Group - Non Ferrous Copper Alloys

Sub Group - UNS C37710 Copper and Copper Zinc Alloy Rod

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Rod

Chemical Composition			Heat Treatment	
Iron	Fe %	0.300 max.	As Raw or Solution Heat Treated	
Lead	Pb %	1.000 - 2.500		
Copper	Cu %	56.500 - 60.000		
Zinc	Zn %	Balance		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
			Mechanical Properties	
			Tensile Strength in Mpa	310 min.
			Yield Strength in Mpa	-
			Elongation in %	20 min.
			Reduction of Area in %	-
			Hardness in BHN	-
			Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
CuZn40Mn1Pb1	DIN	Germany	Rod
2.058	DIN	Germany	Rod
CuZn40Mn1Pb	DIN	Germany	Rod
CuZn40MnPb	DIN	Germany	Rod
SoMs58Pb	DIN	Germany	Rod
CU6	EN	European Union	Rod, Bolt, Screw, Stud and Nut
CuZn40Mn1Pb1	UNI	Italy	Rod

**Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email [marketing@gravitycastindia.com](mailto:marketing@gravitycastindia.com)**

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.