



GRAVITY CAST PVT. LTD.
GRAVITY GROUP OF COMPANIES

Material - UNS N06600

Standard Specification for Ni-Cr Alloy Solid Solution Strengthened

Group - Non-Ferrous Nickel Alloys

Sub Group - UNS N06600 Ni-Cr Alloy Solid Solution Strengthened

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Pipe Flange, Fitting and Valve

| Chemical Composition | | | Heat Treatment | |
|----------------------|------|-----------------|--------------------------------------|----------|
| Carbon | C % | 0.150 max. | As-Cast or Annealing or Age Hardning | |
| Silicon | Si % | 0.500 max. | | |
| Manganese | Mn % | 1.000 max. | | |
| Chromium | Cr % | 14.000 - 17.000 | | |
| Copper | Cu % | 0.500 max. | | |
| Sulphur | S % | 0.015 max. | | |
| Iron | Fe % | 6.000 - 10.000 | | |
| Nickel | Ni % | 72.000 min. | | |
| - | - | - | | |
| | | | Mechanical Properties | |
| - | - | - | Tensile Strength in Mpa | 620 min. |
| - | - | - | Yield Strength in Mpa | 250 min. |
| - | - | - | Elongation in % | 47 min. |
| - | - | - | Reduction of Area in % | - |
| - | - | - | Hardness in BHN | - |
| - | - | - | Impact in Joule | - |

| Cross Reference Table | | | |
|-----------------------|----------|---------|--------------------------------|
| Material | Standard | Country | Grade Belong to the Industry |
| HARPER 600 | SAE | USA | Pipe Flange, Fitting and Valve |
| Inconel 600 | SAE | USA | Pipe Flange, Fitting and Valve |
| NIREX | SAE | USA | Pipe Flange, Fitting and Valve |
| PYROMET 600 | SAE | USA | Pipe Flange, Fitting and Valve |
| SIMALLOY 600 | SAE | USA | Pipe Flange, Fitting and Valve |
| - | - | - | - |
| - | - | - | - |

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.

ONE STOP SOLUTION FOR METAL PARTS