

## Material - UNS N06626

## Standard Specification for Nickel and Nickel-Related Alloys

Group - Non-Ferrous Nickel Alloys

Sub Group - SAE 5879 Nickel and Nickel-Related Alloys

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Sheet, Strip and Foil

Chemical Composition			Heat Treatment	
Carbon	C %	0.030 max.		
Silicon	Si %	0.150 max.		
Manganese	Mn %	0.500 max.	As-Cast or Annealing or Age Hardning	
Chromium	Cr %	20.000 - 23.000		
Molybdenum	Mo %	8.000 - 10.000		
Iron	Fe %	5.000 max.		
Aluminium	Al %	0.400 max.		
Cobalt	Co %	1.000 max.		
Phosphorus	Р%	0.015 max.	Mechanical Properties	
Sulphur	S %	0.015 max.	Tensile Strength in Mpa	827 min.
Titanium	Ti %	0.400 max.	Yield Strength in Mpa	417 min.
Niobium	Nb %	3.150-4.150	Elongation in %	40 min.
Nitrogen	N %	0.020 max.	Reduction of Area in %	-
Nickel	Ni %	Balance	Hardn <mark>ess in BH</mark> N	-
-	-	-	Impac <mark>t in Joule</mark>	-

Cross Reference Table				
Material	Standard	Country	Grade Belong to the Industry	
Inconel 625 LCF	Gravity	India	Sheet, Strip and Foil	
5879	SAE	USA	Sheet, Strip and Foil	
-	-	-	-	
-	-	-	-	
-	-	-	-	
-	-	-	-	
-	-	-	-	

## Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.

## ONE STOP SOLUTION FOR METAL PARTS