



Material - UNS N09706

Standard Specification for Nickel Alloy, Corrosion and Heat-Resistant, Bars, Forgings, Flash Welded Rings and Forging Stock

Group - Non-Ferrous Nickel Alloys

Sub Group - UNS N09706 Nickel Alloy, Corrosion and Heat-Resistant, Bars, Forgings, Flash Welded Rings and

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Bar, Ring and Forging Stock

Chemical Composition			Heat Treatment	
Carbon	C %	0.060 max.	As-Cast or Annealing or Age Hardning	
Silicon	Si %	0.350 max.		
Manganese	Mn %	0.350 max.		
Chromium	Cr %	14.500 - 17.500		
Copper	Cu %	0.300 max.		
Sulphur	S %	0.015 max.		
Aluminium	Al %	0.400 max.		
Niobium	Nb %	2.500 - 3.300		
Titanium	Ti %	1.500 - 2.000		
Phosphorus	P %	0.020 max.		
Boron	B %	0.006 max.		
Nickel	Ni %	39.000 - 44.000		
Iron	Fe %	Balance		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
Inconel 706	SAE	USA	Bar, Ring and Forging Stock
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.