



Material - UNS N10276

Standard Specification for Nickel and Nickel-Related Alloys

Group - Non-Ferrous Nickel Alloys

Sub Group - UNS N10276 Nickel and Nickel-Related Alloys

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.020 max.	As-Cast or Annealing or Age Hardning	
Chromium	Cr %	14.500 - 16.500		
Iron	Fe %	4.000 - 7.000		
Manganese	Mn %	1.000 max.		
Molybdenum	Mo %	15.000 - 17.000		
Silicon	Si %	0.080 max.		
Phosphorus	P %	0.030 max.		
Sulphur	S %	0.030 max.		
Vanadium	V %	0.350 max.		
Tungsten	W %	4.000 max.		
Nickel	Ni %	Balance	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	759 - 1000
-	-	-	Yield Strength in Mpa	462 - 828
-	-	-	Elongation in %	24 - 60
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in HRC	90 - 105
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
Hastelloy C276	SAE	USA	Casting
UNITEMP C 276	SAE	USA	Casting
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.