



GRAVITY CAST PVT. LTD.
GRAVITY GROUP OF COMPANIES

Material - UNS N19907

Standard Specification for Seamless Nickel and Nickel Alloy Pipe, Tube, Sheet, Strip, Plate, Round Bar, Flat Bar, Forging Stock, Hexagon and Wire

Group - Non-Ferrous Nickel Alloys

Sub Group - UNS N19907 Seamless Nickel and Nickel Alloy Pipe, Tube, Sheet, Strip, Plate, Round Bar, Flat Bar, Forging Stock, Hexagon and Wire

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Pipe, Tube, Sheet, Strip, Plate, Hexagon and Wire

Chemical Composition			Heat Treatment	
Aluminium	Al %	0.200 max.	As-Cast or Annealing or Age Hardning	
Cobalt	Co %	12.000 - 16.000		
Niobium	Nb %	4.300 - 5.200		
Titanium	Ti %	1.200 - 1.800		
Carbon	C %	0.060 max.		
Boron	B %	0.012 max.		
Chromium	Cr %	1.000 max.		
Copper	Cu %	0.500 max.		
Manganese	Mn %	1.000 max.		
Sulphur	S %	0.015 max.		
Silicon	Si %	0.350 max.	Mechanical Properties	
Phosphorus	P %	0.015 max.	Tensile Strength in Mpa	1341 min.
Nickel	Ni %	35.000 - 40.000	Yield Strength in Mpa	1120 min.
Iron	Fe %	Balance	Elongation in %	15 min.
-	-	-	Reduction of Area in %	36.500 min.
			Hardness in BHN	-
			Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
Incoloy Alloy 907	Gravity	India	Pipe, Tube, Sheet, Strip, Plate, Hexagon and Wire
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.

ONE STOP SOLUTION FOR METAL PARTS