

Material - UNS R30035

Standard Specification for Cobalt-Based alloy

Group - Non-Ferrous Cobalt Alloys

Sub Group - UNS R30035 Cobalt-Based alloy

Application - Intended for Valve, Pump, General Engineering, Automotive, Medical and other Industries Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.025 max.		
Chromium	Cr %	19.000 - 21.000		
Molybdenum	Mo %	9.000 - 10.500	As-Cast or Annealing	
Nickel	Ni %	33.000 - 37.000		
Iron	Fe %	1.000 max.		
Silicon	Si %	0.150 max.		
Manganese	Mn %	0.150 max.		
Phosphorus	Р%	0.015 max.		
Sulphur	S %	0.010 max.	Mechanical Properties	
Titanium	Ti %	1.000 max.	Tensile Strength in Mpa	793 - 2482
Cobalt	Co %	Balance	Yield Strength in Mpa	241 - 586
-	-	-	Elongation in %	1.800 min.
-	-	-	Reduction of Area in %	35 min.
-	-	-	Hardn <mark>ess in HR</mark> C	43 min.
-	-	-	Impac <mark>t in Joule</mark>	-

Cross Reference Table				
Material	Standard	Country	Grade Belong to the Industry	
F562 R30035	ASTM	USA	Casting	
F 2527 R30035	ASTM	USA	Casting	
-	-	-	-	
-	-	-	-	
-	-	-	-	
-	-	-	-	
-	-	-	-	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.

ONE STOP SOLUTION FOR METAL PARTS