



## Material - UNS R30103

## Standard Specification for Cobalt-Based alloy

**Group - Non-Ferrous Cobalt Alloys** 

Sub Group - UNS R30103 Cobalt-Based alloy

Application - Intended for Valve, Pump, General Engineering, Automotive, Medical and other Industries Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Carbon	C %	2.000 - 2.800		
Iron	Fe %	5.000 max.		
Manganese	Mn %	2.000 max.	As-Cast or Annealing	
Nickel	Ni %	3.500 max.		
Silicon	Si %	2.000 max.		
Chromium	Cr %	28.000 - 33.000		
Boron	В %	0.100 - 1.000		
Tungsten	W %	11.000 - 14.000		_
Cobalt	Co %	Balance	Mechanical Properties	
-	-		Tensile Strength in Mpa	490 - 551.6
-	-	-	Yield Strength in Mpa	-
-	-	-	Elongation in %	1 max.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in HRC	48 - 63
-	-	-	Impac <mark>t in Joule</mark>	-

Cross Reference Table				
Material	Standard	Country	Grade Belong to the Industry	
Stellite 3	Gravity	India	Casting	
-	-	·	-	
-	-	-	-	
-	-	-	-	
-	-	-	-	
-	-	-	-	
-	-	-	-	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.